



URSA TERRA Plus

Espesor 40 mm

Resistencia térmica 1,10 m²·K/W

Declaración Ambiental de Producto

Parámetro Evaluado	Unidad	Fabricación de los materiales			Fin de vida		
		Produccion	Transporte	Instalacion	Transporte	Proceso	Vertedero
		A1 a A3	A4	A5	C2	C3	C4
Global Warming Potential	Kg CO ₂ equiv.	1,43E+00	6,07E-01	1,55E-01	4,73E-03	0,00E+00	1,77E-02
Stratospheric Ozone Layer Depletion Potential	Kg CFC11 equiv.	9,32E-08	1,16E-09	1,63E-10	9,07E-12	0,00E+00	1,51E-10
Acidification Potential	Kg SO ₂ equiv.	8,30E-03	3,96E-03	4,85E-05	2,93E-05	0,00E+00	7,54E-05
Eutrophication Potential	Kg PO ₄ ³⁻ equiv.	1,09E-03	6,30E-04	2,92E-04	4,63E-06	0,00E+00	9,94E-06
Abiotic Resource Depletion Potential	Kg Sb equiv.	1,12E-02	4,08E-03	4,46E-05	3,19E-05	0,00E+00	6,74E-05
Photochemical Ozone Formation Potential	Kg ethane equiv.	5,87E-04	3,58E-04	4,66E-05	2,49E-06	0,00E+00	1,20E-05
Consumption of renewable primary energy	MJ (lower heating value)	2,52E+00	1,58E-02	4,76E-03	1,24E-04	0,00E+00	9,82E-03
Consumption of non-renewable primary energy	MJ (lower heating value)	2,65E+01	8,53E+00	9,89E-02	6,66E-02	0,00E+00	1,46E-01
Use of non-renewable secondary fuels	MJ (lower heating value)	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
Use of renewable secondary fuels	MJ (lower heating value)	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
Fresh water consumption	m ³	1,21E-02	2,50E-04	8,39E-05	1,96E-06	0,00E+00	2,42E-04
Waste production:	Kg	2,24E+00	2,76E-02	2,26E-01	2,15E-04	0,00E+00	9,28E-01
· hazardous	Kg	8,45E-03	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
· non hazardous	Kg	2,23E+00	2,76E-02	2,26E-01	2,15E-04	0,00E+00	9,28E-01
· radioactive	Kg	1,23E-03	1,54E-05	2,88E-08	1,21E-07	0,00E+00	0,00E+00
Output materials for	Kg	1,12E-01	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
· Reusing	Kg	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
· Recycling	Kg	1,12E-01	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
· Energy Recovery	Kg	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00