



URSA TERRA Plus

Espesor 50 mm

Resistencia térmica 1,35 m²·K/W

Declaración Ambiental de Producto

| Parámetro Evaluado | Unidad | Fabricación de los materiales | | | Fin de vida | | |
|---|---|-------------------------------|------------|-------------|-------------|----------|-----------|
| | | Produccion | Transporte | Instalacion | Transporte | Proceso | Vertedero |
| | | A1 a A3 | A4 | A5 | C2 | C3 | C4 |
| Global Warming Potential | Kg CO ₂ equiv. | 1,78E+00 | 7,58E-01 | 1,94E-01 | 5,91E-03 | 0,00E+00 | 2,21E-02 |
| Stratospheric Ozone Layer Depletion Potential | Kg CFC11 equiv. | 1,16E-07 | 1,45E-09 | 2,04E-10 | 1,13E-11 | 0,00E+00 | 1,89E-10 |
| Acidification Potential | Kg SO ₂ equiv. | 1,03E-02 | 4,95E-03 | 6,06E-05 | 3,66E-05 | 0,00E+00 | 9,42E-05 |
| Eutrophication Potential | Kg PO ₄ ³⁻ equiv. | 1,36E-03 | 7,87E-04 | 3,65E-04 | 5,79E-06 | 0,00E+00 | 1,24E-05 |
| Abiotic Resource Depletion Potential | Kg Sb equiv. | 1,38E-02 | 5,10E-03 | 5,57E-05 | 3,98E-05 | 0,00E+00 | 8,42E-05 |
| Photochemical Ozone Formation Potential | Kg ethane equiv. | 7,24E-04 | 4,47E-04 | 5,82E-05 | 3,11E-06 | 0,00E+00 | 1,50E-05 |
| Consumption of renewable primary energy | MJ (lower heating value) | 2,66E+00 | 1,97E-02 | 5,94E-03 | 1,54E-04 | 0,00E+00 | 1,23E-02 |
| Consumption of non-renewable primary energy | MJ (lower heating value) | 3,28E+01 | 1,07E+01 | 1,24E-01 | 8,32E-02 | 0,00E+00 | 1,82E-01 |
| Use of non-renewable secondary fuels | MJ (lower heating value) | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 |
| Use of renewable secondary fuels | MJ (lower heating value) | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 |
| Fresh water consumption | m3 | 1,51E-02 | 3,12E-04 | 1,05E-04 | 2,45E-06 | 0,00E+00 | 3,02E-04 |
| Waste production: | Kg | 2,80E+00 | 3,44E-02 | 2,82E-01 | 2,68E-04 | 0,00E+00 | 1,16E+00 |
| · hazardous | Kg | 1,05E-02 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 |
| · non hazardous | Kg | 2,79E+00 | 3,44E-02 | 2,82E-01 | 2,68E-04 | 0,00E+00 | 1,16E+00 |
| · radioactive | Kg | 1,53E-03 | 1,92E-05 | 3,60E-08 | 1,51E-07 | 0,00E+00 | 0,00E+00 |
| Output materials for | Kg | 1,40E-01 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 |
| · Reusing | Kg | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 |
| · Recycling | Kg | 1,40E-01 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 |
| · Energy Recovery | Kg | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 | 0,00E+00 |